



RBS CARBON TO C-T PLATEBATTEN CONVERSION TABLE (FULL LENGTH)

Manufacturer	Material	Code	Leech EI (NM^2)	Weight (grams/m)	Width (mm)	Thickness (mm)
	Carbon	CTP10320	2.7	46	10	3.2
	Carbon	CB10120	2.9	47	10	3.0
	Carbon	CTP15320	4.0	70	15	3.2
	Carbon	CTP10380	4.6	55	10	3.8
	Carbon	CTP19320	5.1	88	19	3.2
	Carbon	CB10150	5.6	61	10	3.8
	Carbon	CTP25320	6.7	116	25	3.2
	Carbon	CTP15380	7.0	83	15	3.8
	Carbon	CTP10440	7.4	64	10	4.4
	Carbon	CTP19380	8.8	105	19	3.8
	Carbon	CTP15440	11.1	96	15	4.4
	Carbon	CTP25380	11.6	138	25	3.8
	Carbon	CB10200	12.2	79	10	5.1
	Carbon	CTP19440	14.1	122	19	4.4
	Carbon	CB15150	14.7		15	3.8
	Carbon	CTP10560	16.0	83	10	5.6
	Carbon	CTP25440	18.6	160	25	4.4
	Carbon	CB15200	19.8	122	15	5.1
	Carbon	CB10250	23.8	98	10	6.4
	Carbon	CTP15560	24.0	124	15	5.6
	Carbon	CB19200	25.1	151	19	5.1
	Carbon	CTP10680	29.4	101	10	6.8
	Carbon	CTP19560	30.4	157	19	5.6
	Carbon	CB15250	35.8	150	15	6.4
	Carbon	CTP25560	40.0	207	25	5.6
	Carbon	CB19250	42.5	182	19	6.4
	Carbon	CTP15680	44.1	152	15	6.8
	Carbon	CB15300	54.4	168	15	7.6
	Carbon	CTP19680	55.9	192	19	6.8
	Carbon	CB25250	56.1	240	25	6.4
	Carbon	CTP15800	73.3	178	15	8.0
	Carbon	CTP25680	73.5	253	25	6.8
	Carbon	CB19300	79.4	218	19	7.6
	Carbon	CB38250	89.0	365	38	6.4
	Carbon	CTP19800	92.8	225	19	8.0
	Carbon	CB25300	98.7	284	25	7.6
	Carbon	CTP15920	113.0	204	15	9.2
	Carbon	CB19350	122.1	253	19	8.9
	Carbon	CTP25800	122.1	296	25	8.0
	Carbon	CTP19920	143.1	259	19	9.2
	Carbon	CB25350	158.0	329	25	8.9
	Carbon	CB38300	160.1	438	38	7.6
	Carbon	CB19400	185.3	292	19	10.2
	Carbon	CTP25920	188.4	341	25	9.2
	Carbon	CB25400	243.3	382	25	10.2
	Carbon	CB38350	257.0	507	38	8.9
	Carbon	CB38400	384.2	588	38	10.2
	Carbon/S-glass	CT22	>50			

To order C-T PlateBattens use the website form at:
www.sailbattens.com/orders_ctplate.htm



RBS GLASS TO C-T PLATEBATTEN CONVERSION TABLE (FULL LENGTH)

Manufacturer	Material	Code	Leech EI (NM^2)	Weight (grams/m)	Width (mm)	Thickness (mm)
	Carbon	CTP10320	2.7	46	10	3.2
	Glass	E10180	3.1	85	10	4.6
	Glass	E15160	3.5	117	15	4.1
	Carbon	CTP15320	4.0	70	15	3.2
	Glass	E10200	4.3	95	10	5.1
	Carbon	CTP10380	4.6	55	10	3.8
	Glass	E15180	4.8	130	15	4.6
	Carbon	CTP19320	5.1	88	19	3.2
	Carbon	CTP25320	6.7	116	25	3.2
	Glass	E10230	6.8	110	10	5.8
	Carbon	CTP15380	7.0	83	15	3.8
	Glass	E15200	7.4	148	15	5.1
	Carbon	CTP10440	7.4	64	10	4.4
	Glass	E19200	8.4	185	19	5.1
	Carbon	CTP19380	8.8	105	19	3.8
	Glass	E10265	9.7	127	10	6.7
	Glass	E15230	9.7	165	15	5.9
	Carbon	CTP15440	11.1	96	15	4.4
	Glass	E19230	11.4	206	19	5.9
	Carbon	CTP25380	11.6	138	25	3.8
	Carbon	CTP19440	14.1	122	19	4.4
	Glass	E10300	14.6	146	10	7.6
	Glass	E15265	14.7	192	15	6.7
	Carbon	CTP10560	16.0	83	10	5.6
	Glass	E19265	17.9	239	19	6.7
	Carbon	CTP25440	18.6	160	25	4.4
	Glass	E15300	21.1	215	15	7.6
	Carbon	CTP15560	24.0	124	15	5.6
	Glass	E25265	24.5	323	25	6.7
	Glass	E19300	26.0	275	19	7.6
	Carbon	CTP10680	29.4	101	10	6.8
	Carbon	CTP19560	30.4	157	19	5.6
	Glass	E25300	34.1	362	25	7.6
	Carbon	CTP25560	40.0	207	25	5.6
	Glass	E19350	41.9	320	19	8.9
	Carbon	CTP15680	44.1	152	15	6.8
	Glass	E25350	54.9	424	25	8.9
	Carbon	CTP19680	55.9	192	19	6.8
	Glass	E19400	60.3	364	19	10.2
	Carbon	CTP15800	73.3	178	15	8.0
	Carbon	CTP25680	73.5	253	25	6.8
	Glass	E25400	79.4	485	25	10.2
	Carbon	CTP19800	92.8	225	19	8.0
	Carbon	CTP15920	113.0	204	15	9.2
	Carbon	CTP25800	122.1	296	25	8
	Carbon	CTP19920	143.1	259	19	9.2
	Glass	E25500	152.1	592	25	12.7
	Carbon	CTP25920	188.4	341	25	9.2

To order C-T PlateBattens use the website form at:
www.sailbattens.com/orders_ctplate.htm